

# Scientists report first solar cell producing more electrons in photocurrent than solar photons entering cell

December 15 2011

---

(PhysOrg.com) -- Researchers from the National Renewable Energy Laboratory (NREL) have reported the first solar cell that produces a photocurrent that has an external quantum efficiency greater than 100 percent when photoexcited with photons from the high energy region of the solar spectrum.

The external [quantum efficiency](#) for photocurrent, usually expressed as a percentage, is the number of electrons flowing per second in the external circuit of a solar cell divided by the number of photons per second of a specific energy (or wavelength) that enter the solar cell. None of the solar cells to date exhibit external photocurrent quantum efficiencies above 100 percent at any wavelength in the solar spectrum.

The external quantum efficiency reached a peak value of 114 percent. The newly reported work marks a promising step toward developing Next Generation Solar Cells for both solar electricity and solar fuels that will be competitive with, or perhaps less costly than, energy from fossil or nuclear fuels.

## Multiple Exciton Generation is key to making it possible

A paper on the breakthrough appears in the Dec. 16 issue of Science Magazine. Titled “Peak External Photocurrent Quantum Efficiency

Exceeding 100 percent via MEG in a Quantum Dot Solar Cell,” it is co-authored by NREL scientists Octavi E. Semonin, Joseph M. Luther, Sukgeun Choi, Hsiang-Yu Chen, Jianbo Gao, Arthur J. Nozik and Matthew C. Beard. The research was supported by the Center for Advanced Solar Photophysics, an Energy Frontier Research Center funded by the DOE Office of Science, Office of Basic Energy Sciences. Semonin and Nozik are also affiliated with the University of Colorado at Boulder.

The mechanism for producing a quantum efficiency above 100 percent with solar photons is based on a process called Multiple Exciton Generation (MEG), whereby a single absorbed photon of appropriately high energy can produce more than one electron-hole pair per absorbed photon.

NREL scientist Arthur J. Nozik first predicted in a 2001 publication that MEG would be more efficient in semiconductor quantum dots than in bulk semiconductors. Quantum dots are tiny crystals of semiconductor, with sizes in the nanometer (nm) range of 1-20 nm, where 1 nm equals one-billionth of a meter. At this small size, semiconductors exhibit dramatic effects because of quantum physics, such as:

- rapidly increasing bandgap with decreasing quantum dot size,
- formation of correlated electron-hole pairs (called excitons) at room temperature,
- enhanced coupling of electronic particles (electrons and positive holes) through Coulombic forces,
- and enhancement of the MEG process.

Quantum dots confine the charges and harvest excess energy

Quantum dots, by confining charge carriers within their tiny volumes, can harvest excess energy that otherwise would be lost as heat – and therefore greatly increase the efficiency of converting photons into

usable free energy.

The researchers achieved the 114 percent external quantum efficiency with a layered cell consisting of antireflection-coated glass with a thin layer of a transparent conductor, a nanostructured zinc oxide layer, a quantum dot layer of lead selenide treated with ethanedithol and hydrazine, and a thin layer of gold for the top electrode.

In a 2006 publication, NREL scientists Mark Hanna and Arthur J. Nozik showed that ideal MEG in solar cells based on quantum dots could increase the theoretical thermodynamic power conversion efficiency of solar cells by about 35 percent relative to today's conventional solar cells. Furthermore, the fabrication of Quantum Dot Solar Cells is also amenable to inexpensive, high-throughput roll-to-roll manufacturing.

Such potentially highly efficient cells, coupled with their low cost per unit area, are called Third (or Next) Generation Solar Cells. Present day commercial photovoltaic solar cells are based on bulk semiconductors, such as silicon, cadmium telluride, or copper indium gallium (di)selenide; or on multi-junction tandem cells drawn from the third and fifth (and also in some cases fourth) columns of the Periodic Table of Elements. All of these cells are referred to as First- or Second-Generation Solar Cells.

## **First experiment to show 100-percent-plus in operating solar cells**

MEG, also referred to as Carrier Multiplication (CM), was first demonstrated experimentally in colloidal solutions of quantum dots in 2004 by Richard Schaller and Victor Klimov of the DOE's Los Alamos National Laboratory. Since then, many researchers around the world, including teams at NREL, have confirmed MEG in many different

semiconductor quantum dots. However, nearly all of these positive MEG results, with a few exceptions, were based on ultrafast time-resolved spectroscopic measurements of isolated quantum dots dispersed as particles in liquid colloidal solutions.

The new results published in *Science* by the NREL research team is the first report of MEG manifested as an external photocurrent quantum yield greater than 100 percent measured in operating quantum dot solar cells at low light intensity; these cells showed significant power conversion efficiencies (defined as the total power generated divided by the input power) as high as 4.5 percent with simulated sunlight. While these [solar cells](#) are un-optimized and thus exhibit relatively low power conversion efficiency (which is a product of the photocurrent and photovoltage), the demonstration of MEG in the photocurrent of a solar cell has important implications because it opens new and unexplored approaches to improve solar cell efficiencies.

Another important aspect of the new results is that they agree with the previous time-resolved spectroscopic measurements of MEG and hence validate these earlier MEG results. Excellent agreement follows when the external quantum efficiency is corrected for the number of photons that are actually absorbed in the photoactive regions of the cell. In this case, the determined quantum yield is called the internal quantum efficiency. The internal quantum efficiency is greater than the external quantum efficiency because a significant fraction of the incident [photons](#) are lost through reflection and absorption in non-photocurrent producing regions of the cell. A peak internal quantum yield of 130% was found taking these reflection and absorption losses into account.

**More information:** Peak External Photocurrent Quantum Efficiency Exceeding 100% via MEG in a Quantum Dot Solar Cell, *Science* 16 December 2011: Vol. 334 no. 6062 pp. 1530-1533. [DOI: 10.1126/science.1209845](https://doi.org/10.1126/science.1209845)

**ABSTRACT**

Multiple exciton generation (MEG) is a process that can occur in semiconductor nanocrystals, or quantum dots (QDs), whereby absorption of a photon bearing at least twice the bandgap energy produces two or more electron-hole pairs. Here, we report on photocurrent enhancement arising from MEG in lead selenide (PbSe) QD-based solar cells, as manifested by an external quantum efficiency (the spectrally resolved ratio of collected charge carriers to incident photons) that peaked at  $114 \pm 1\%$  in the best device measured. The associated internal quantum efficiency (corrected for reflection and absorption losses) was 130%. We compare our results with transient absorption measurements of MEG in isolated PbSe QDs and find reasonable agreement. Our findings demonstrate that MEG charge carriers can be collected in suitably designed QD solar cells, providing ample incentive to better understand MEG within isolated and coupled QDs as a research path to enhancing the efficiency of solar light harvesting technologies.

Provided by National Renewable Energy Laboratory

Citation: Scientists report first solar cell producing more electrons in photocurrent than solar photons entering cell (2011, December 15) retrieved 17 May 2024 from <https://phys.org/news/2011-12-scientists-solar-cell-electrons-photocurrent.html>

This document is subject to copyright. Apart from any fair dealing for the purpose of private study or research, no part may be reproduced without the written permission. The content is provided for information purposes only.